

CERMIPROOF SF

CEMENT BASED, 2 COMPONENT, SEMI-ELASTIC WATERPROOFING MATERIAL



Gray



- *Ideal solution for waterproofing under ceramic tiles in residences*
- *Suitable for horizontal and vertical applications*
- *Easy to apply*
- *Non-corrosive and non-toxic*

PRODUCT INFORMATION

WHERE TO USE

- Before the application of ceramic tiles, especially in wet areas such as bathrooms, WCs, shower, balconies.
- For waterproofing applications to be made on cement-based surfaces such as concrete, plaster, screed etc. indoors and outdoors.

GENERAL FEATURES

Nature of Material	: Contains high quality cement, It contains water impermeability additives and liquid polymer.
Type	: Powder+liquid
Colour	: Gray
Density	: $1.80 \pm 0.1 \text{ gr/cm}^3$ (mixture)

TECHNICAL CHARACTERISTICS(*)

Temperature resistance	: - 30 °C +70 °C
Tensile strength	
- Initial tensile adhesion	: $\geq 0,5 \text{ Mpa (N/mm}^2)$
- After contact with water	: $\geq 0,5 \text{ Mpa (N/mm}^2)$
- After heat ageing	: $\geq 0,5 \text{ Mpa (N/mm}^2)$
- After freeze-thaw cycle	: $\geq 0,5 \text{ Mpa (N/mm}^2)$
Crack-bridging	: $\geq 0,75 \text{ mm}$
Waterproofing	: $\geq 1,5 \text{ bar}$

(On positive side)

(*) These values are results of laboratory tests and they are performance values recorded 28 days after the finished applications.

STANDARDS AND DOCUMENTS

- TS EN 14891
- CE
- Public Works Pos. No. 10.300.2173



CONSUMPTION


- 1,4-1,6 kg/m² for 1 mm thickness

PACKAGING

- In set of kraft bags, 20kg, (component A); plastic drum 5 l (component B)

STORAGE

- Moisture-free, dry and protected against external weather conditions should be stocked in warehouses.
- Shelf life is 1 year under suitable storage conditions.
- Opened packages should be kept tightly closed.



APPLICATION

APPLICATION PROCEDURE

Pot life: Maximum 3 hours

Application temperature: +5 °C , +35 °C

Application thickness: 2-3 mm

Wait time between coats: Minimum 6 hours

Wait time prior to ceramic application: Minimum 2 days

Time for gaining mechanical strength: 2 days

Time to become waterproof: 7 days

(*) These values are results of laboratory tests and they are performance values recorded 28 days after the finished applications.

SUBSTRATE PREPARATION

- The application surface must be clean, free of dirt, free from dust and loose particles.
- The surface should not be too dry or completely wet before application.
- Apply **CERMIFFILM** primer to the surface prior to application of the product to improve adhesion to the surface and wait 1 hours for the primer to dry.
- Reduce the surface temperature by moistening the surface with water spray method prior to application on surfaces exposed to direct sunlight or on overheated surfaces.
- Remove and repair any defects, cracks and holes on the application surface properly by using the repair mortars of **CERMIMORTAR** or **CERMIREP**.
- In cases where chamfer tape cannot be used, chamfer the wall-floor joints with **CERMIREP** repair mortars before application.

APPLICATION

- Liquid component of 5 l for 20 kg mixture.
- Mix the product a low-speed (400 rpm) mixer until the mixture is homogeneous and free of lumps.
- Allow the mixture to rest for 3 minutes prior to application and apply after mixing it again.
- The prepared mixture should be applied to the surface with a hard brush in minimum 2 coats. The first coat should be applied from right to left or top to bottom and our **CERMITAPE TPE** should be used at wall-floor joints.
- The second coat should be applied 6 hours after the application of the first coat in the opposite direction to the first one. The main objective here is to cover the surface with the entire material.
- Proceed to the next stage after waterproofing after minimum 2 days.
- The application information and the times given in the steps are under different ambient conditions (low/high temperature, humidity, wind, etc.) may be prolonged.

RECOMMENDATIONS

- The mixing ratio of components A and B is shown on the package and a different mixing ratio should not be used. You must not add water and another material add to the product.
- Do not use the product if you encounter problems of precipitation and petrification after unpacking the product.
- Do not apply directly on the metal, rubber, PVC, wooden, cement-based chipboard and aerated concrete surfaces.
- It has been developed for waterproofing applications under **CERMIPROOF SF** coating and for positive purposes, it should be made open and must be covered with a suitable coating material.
- Surfaces applied with the product should be protected from direct sunlight, rain and frost for minimum 1 day.

SAFETY INSTRUCTIONS

- As it is cement based, do not inhale and avoid of its contact with skin and eyes.
- It is recommended to use appropriate work equipment (gloves, goggles, mask, knee pads, etc.) during application of the product.
- For more detailed information please read the Material Safety Data Sheet (MSDS).



Note: Note: Technical values and application instructions are valid under ambient temperature of 23°C with relative humidity 50% and they are the results of our tests and experience in accordance with international standards. Our company is not responsible for any errors that may occur if the instructions and recommendations specified in the technical data sheets are not followed.

CERMIX

CERMIX Produced by Koramic Yapı Kimyasalları under license of Cermix SA. www.cermix.com.tr • www.koramic.com.tr

Genel Merkez
Koramic Yapı Kimyasalları San. Tic. A.Ş.
E-5 Karayolu Üzeri, Şifa Mah. Hükümet Cad.
Tuzla 34941 İstanbul / TÜRKİYE
Tel: +90.216.423 34 33 • Faks: +90.216.423 53 63

Bozüyük Fabrika
Bozüyük Organize San. Böl. 10. Cad.
106 Ada / 5 Parsel No: 3 Bozüyük - BİLEÇİK / TÜRKİYE
Phone: +90.228.314 63 00
Faks: +90.228.314 63 0

Tarsus Fabrika
Huzurkent Tarsus Organize Sanayi Bölgesi
13. Cadde No: 10 Tarsus - MERSİN / TÜRKİYE
Phone: +90.324.676 40 41-676 42 32-676 44 49
Faks: +90.324.676 40 47