

# CERMITHANE PC 2C

## POLYMER BASED, TAR MODIFIED 2 COMPONENT EXPANSION and SEALING SEALANT



Black



- Jet fuels, hydraulic oils, sea water resistant
- Cold applied
- High elastic
- Waterproof
- Long lasting

## PRODUCT INFORMATION

### WHERE TO USE

- Joints on airport runways, highways and bridges gaps, repairing and insulating cracks
- Ports, large parking areas, loading areas
- Fuel stations, petrochemical etc. in industrial areas it is suitable for use.

### GENERAL FEATURES

**Chemical nature** : Modified with tar polymer based sealant  
**Density** :  $1,38 \pm 0,03$  gr/ml (ASTM D1475)  
**Colour** : Black  
**Viscosity** : 10000-14000 cP (ASTM D2196-86)

### TECHNICAL CHARACTERISTICS

**Elongation at Break** :  $> \% 650$  (ASTM D412)  
**Tensile Strength (ISO 37)** :  $> 0,65$  Mpa (ASTM D412)  
**Shore A Hardness (ISO 868)** : 15-20 (ASTM D2240) ,7 days

### CONSUMPTION

- 2.2 linear meter / kg (20 mm joint width, 15 mm joint for depth)


### PACKAGING

- 12 kg (10 kg + 2 kg) metal bucket (60 pieces on pallet)



### STORAGE

- Moisture-free, dry and protected against external weather conditions should be stocked in warehouses.
- Shelf life is 1 year under appropriate storage conditions.
- Opened packages should be kept tightly closed.



## APPLICATION

### SUBSTRATE PREPARATION

- **CERMITHANE PC 2C** using polyethylene suppositories, it is prevented from sticking to the joint bottoms. This is a two-way movement gives ability.
- The size of the polyethylene wick is 20-25% of the joint diameter must be large.

### APPLICATION

- Component A is mixed in itself, then component B is added. It is mixed very well until a homogeneous color is obtained.
- Min. 300-400 rpm power mechanical mixers should be used.
- Injecting into the joint without creating air bubbles is done.



### RECOMMENDATIONS

- In closed areas due to long-term solvent smell should not be applied or the environment should be well ventilated.
- In cold weather, packages should be applied for at least 24 hours. It should be stored at +15 °C first.
- After the application, water, rain, snow etc. effects should be protected.
- Full mechanical and chemical resistance within 7 days occur should be taken into account.

### SAFETY INSTRUCTIONS

- It should not be inhaled, and eye contact should be avoided.
- It is recommended to use appropriate work equipment (gloves, goggles, mask, knee pads, etc.) during application of the product.
- For more detailed information please read the Material Safety Data Sheet (MSDS)

**Note:** Technical values and application instructions are valid under ambient temperature of 23°C with relative humidity 50% and they are the results of our tests and experience in accordance with international standards. Our company is not responsible for any errors that may occur if the instructions and recommendations specified in the technical data sheets are not followed.

**CERMIX**

CERMIX Produced by Koramic Yapı Kimyasalları under license of Cermix SA. [www.cermix.com.tr](http://www.cermix.com.tr) \* [www.koramic.com.tr](http://www.koramic.com.tr)

Head Office  
Koramic Yapı Kimyasalları San. Tic. A.Ş.  
E-5 Karayolu Üzeri, Sıfı Mah. Hükümet Cad.  
Tuzla 34941 İstanbul / TÜRKİYE  
Phone: +90.216.423 34 33 • Fax: +90.216.423 53 63

Bozüyük Factory  
Bozüyük Organize San. Böl. 10. Cad.  
106 Ada / 5 Parsel No: 3 Bozüyük - BİLEÇİK / TÜRKİYE  
Phone: +90.228.314 63 00  
Fax: +90.228.314 63 0

Tarsus Factory  
Huzurkent Tarsus Organize Sanayi Bölgesi  
13. Cadde No: 10 Tarsus - MERSİN / TÜRKİYE  
Phone: +90.324.676 40 41-676 42 32-676 44 49  
Fax: +90.324.676 40 47