

CERMIPOOL

CEMENT-BASED HIGH PERFORMANCE, SPECIALLY DEVELOPED FOR POOL, S1 CLASS, ELASTIC ADHESIVE MORTAR



Grey



White



- *Excellent adhesion performance in pools and wet areas*
- *Possibility to lay ceramic tiles from top to bottom without slipping*

- *High resistance to thermal shocks and surface movements due to its flexibility*
- *Making labor easier with long working time*
- *Improved water repellency*

PRODUCT INFORMATION

WHERE TO USE

- Bonding of porcelain ceramic, granite ceramic, natural stone, glass mosaic, ceramic, marble etc. coating materials,
- In wet areas such as pools, water tanks, baths, car wash stations, etc,
- Ceramic applications on difficult surfaces such as paint, plaster, ceramic etc,
- Indoor and outdoor applications on cement based surfaces such as concrete, plaster, screed etc.

GENERAL FEATURES

- Nature** : Powder product containing high quality cement, filler and performance-enhancing, water repellency polymer additives.
- Colour** : Grey / White
- Density** : $1.3 \pm 0.05 \text{ g/cm}^3$

TECHNICAL CHARACTERISTICS (*)

Tensile strength

- Initial (after 28 days) : $\geq 1 \text{ Mpa (N/mm}^2\text{)}$
- After heat ageing : $\geq 1 \text{ Mpa (N/mm}^2\text{)}$
- After water ageing : $\geq 1 \text{ Mpa (N/mm}^2\text{)}$
- After freeze-thaw cycle : $\geq 1 \text{ Mpa (N/mm}^2\text{)}$
- Open time : $\geq 0.5 \text{ MPa (N/mm}^2\text{)}$

(after 30 minutes)

Shear : $\leq 0.5 \text{ mm}$

Flexibility : $2.5 \text{ mm} \leq S1 \leq 5 \text{ mm}$

Temperature resistance : $-40^\circ\text{C} - +80^\circ\text{C}$

Fire resistance class : A1 (TS EN 13501 – 1)

(*)These values are results of laboratory tests and they are performance values recorded 28 days after the finished applications. The values may vary because of different site conditions.



STANDARDS AND DOCUMENTS

- 12004-1/C2TE, S1 class
- Public works pos. No. : 04.380/008

CONSUMPTION

- 3-6 kg/m² in average

PACKAGING

- In kraft bags, 25 kg, (48 pcs / 1200 kg per palette)

STORAGE

- Maximum 10 kraft bags can be stacked on each other.
- It should be stored in moisture-free, dry warehouses which are well-protected against external weather conditions.
- Shelf life is 1 year under appropriate storage conditions.
- Opened packages should be stored as tightly sealed.



Interior - Exterior



Surface Inspection



Application Temperature



Homogeneous Mixture



Oversized Tile



Application with Notched Trowel



Work Duration



Water Pressure Resistance



Flexible

APPLICATION

APPLICATION PROCEDURE

Mixture ratio: 5.5 – 6.5 l water for 25 kg powder product

Time allowance for working and tile correction: 30 minutes

Time for use of mixture (Pot life): 3 hours

Application temperature: +5°C to +35°C

Time for foot traffic: minimum 24 hours

Pointing time: after minimum 24 hours

SUBSTRATE PREPARATION


- The application surfaces must be free from dust, dirt, oil, etc. and must be dry, smooth and sound.
- Surfaces with high absorbency should be primed with **CERMI FILM** prior to application.
- Overheated surfaces exposed to direct sunlight should be moisturized before application.
- Any surface defects, cracks and holes should be corrected and repaired with **CERMIMORTAR**, **CERMIREP** repair mortars or **CERMI FLOOR** levelling screeds. Surface corrections up to 5mm vertically and 7mm horizontally can be made with **CERMIPOOL**.
- Glossy surfaces such as ceramic, exposed concrete etc. should be primed with **CERMI FILM PLUS** or **CERMI FILM PLUS BETON** prior to application.

APPLICATION

- Slowly add 25 kg of **CERMIPOOL** to 5.5 - 6.5 l (22-26%) of clean water and mix with a low-speed mixer until it becomes homogenous and free of lumps.
- Allow the mixture to rest for 5 minutes, then stir again for 1-2 minutes prior to application.
- When prepared, the mortar should have a consistency that will not flow when taken on the trowel.
- After **CERMIPOOL** is applied to the surface with a toothed steel trowel selected in accordance with the tile size, it should be trowelled to obtain a smooth adhesion surface.
- The working time of **CERMIPOOL** is 30 minutes. However, under different ambient conditions (e.g. low/high temperature, humidity, wind, etc.) the working time may be shorter or longer. For this reason, care should be taken to ensure that the adhesive does not form a film-crust on the surface during application and any film, if any, should be scraped off.
- In order for the adhesion to be firm and the adhesive to be fully spread on the back of the tile, the tile should be lightly tamped by using a rubber mallet.
- The prepared mixture should be consumed within 3 hours.
- For coating materials larger than 40x40 cm, a combined adhesion method (i.e. adhesive application both on the surface and on the back of the tile) should be used. Consumption may increase by 30-50% approximately.
- Proceed to the process of grouting at least 24 hours after the adhesion process.

RECOMMENDATIONS

- After application, wash all tools you used with water and remove off any mortar residues left on the surface with **CERMINET**.
- After application, the surface should be protected from contact with water for at least 24 hours.
- It should not be applied in case of freezing risk or on overheated surfaces, under direct sunlight and in high winds.
- Do not apply directly on difficult surfaces such as metal, PVC, wood, cement-based chipboard etc.; consult technical service for solution.
- Do not apply on newly plastered or concrete surfaces before the curing process is completed.
- For applications to be made on large areas, necessary expansion joints should be allowed considering the thermal stress and mechanical loads that may occur on the surfaces and they should be filled with suitable **CERMITHANE** mastic or **CERMITAPE FPO** expansion profiles.
- Do not use the product if you observe any petrification after unpacking it.
- White coloured adhesives should be used for bonding light coloured and water-absorbent coating materials.
- In case of in wet areas such as pool, bath, terrace etc., waterproofing should be done with **CERMI PROOF FF/FF PLUS** prior to tile application.



SAFETY INSTRUCTIONS

- As it is cement based, do not inhale and avoid of its contact with skin and eyes.
- It is recommended to use appropriate work equipment (gloves, goggles, mask, knee pads, etc.) during application of the product.
- For more detailed information please read the Material Safety Data Sheet (MSDS).

Note: Technical values and application instructions are valid under ambient temperature of 23°C with relative humidity 50% and they are the results of our tests and experience in accordance with international standards. Our company is not responsible for any errors that may occur if the instructions and recommendations specified in the technical data sheets are not followed.

CERMIX

CERMIX Produced by Koramic Yapı Kimyasalları under license of Cermix SA. www.cermix.com.tr * www.koramic.com.tr

Head Office
Koramic Yapı Kimyasalları San. Tic. A.Ş.
E-5 Karayolu Üzeri, Sıfı Mah. Hükümet Cad.
Tuzla 34941 İstanbul / TÜRKİYE
Phone: +90.216.423 34 33 • Fax: +90.216.423 53 63

Bozüyük Factory
Bozüyük Organize San. Böl. 10. Cad.
106 Ada / 5 Parsel No: 3 Bozüyük - BİLEÇİK / TÜRKİYE
Phone: +90.228.314 63 00
Fax: +90.228.314 63 00

Tarsus Factory
Huzurkent Tarsus Organize Sanayi Bölgesi
13. Cadde No: 10 Tarsus - MERSİN / TÜRKİYE
Phone: +90.324.676 40 41-676 42 32-676 44 49
Fax: +90.324.676 40 47