CERMITAPE FPO 1 MM

FLEXIBLE POLYOLEFIN (FPO) BASED DILATATION AND WATERPROOFING TAPE



(DIN EN 12311-2, Metot B)

(DIN FN 12311-2 Metot B)



- High adhesion
- · High elasticity
- Chemical resistance
- Resistant to weather conditions and water
- Root resistant

- UV-resistant
- Plasticiser-free
- Suitable for contact with drinking water

TECHNICAL CHARACTERISTICS

13,2 Mpa

• Expansion joint

Tear Resistance -

Tear Resistance -

UV-Resistance

Reaction to Fire

Lengthwise

PRODUCT INFORMATION

WHERE TO USE

- · Balconies, terraces, parapets,
- •In areas with permanent wet volumes such as pools, water tanks, etc.,
- •In tunnels, foundation-curtain walls,
- •In wall-floor joints, expansion joints.

GENERAL FEATURES

Chemical structure : Flexible Polyolefin (FPO)

Width : 200 mm Colour : Grey

STORAGE

- •Do not open the package in dry and moisture-free environments and It is 12 months from the date of production provided that it is not damaged.
- •If packaging film has been opened apply the material within 2 months.

STANDARDS AND DOCUMENTS

•Tested according to DIN EN ISO 9001:2015

PACKAGING

•One roll 20 meters, 5 rolls per carton







8,8 Mpa Across Elongation at break -%980 (DIN EN 12311-2, Metot B) Lengthwise Elongation at break %800 (DIN EN 12311-2, Metot B)

- Across Tear Resistance(nail 265 N (DIN FN 12310-1) shank) - Lengthwise Tear Resistance(nail 275 N (DIN EN 12310-1) shank) - Across Water vapour per-98 m (DIN EN 1931, Metot B) meability Shore A Hardness ca. 87 >500 hours **Bonding Strength** ≥3,0 Mpa (DIN EN 1348) Peel test on Wood ≥100 N Carrier (DIN EN 1928-A-60 kPa /24 hours Water Tightness (DIN EN 1928-A-400 kPa /72 hours **Burst Presure** ≥3,6 bar

(*)These values were obtained as a result of laboratory tests and are the performance values of the finished applications after 28 days. Values may vary due to the difference in the construction site environment.

(DIN FN 11925-2

FN 13501-1)

>6500 h

Class E



Date of Revision : 05/09/2023 Revision Number: 01

CERMITAPE FPO 1 MM

APPLICATION

APPLICATION PROCEDURE

Thickness: 1 mm Total weight: 1020 g/m² Length per roll: 20 m

Resistance to temperature: -30 °C / + 90 °C

SUBSTRATE PREPARATION

- •In dilatation joints, care should be taken to ensure that the internal and external surfaces are solid, dry, dust-free and clean, in balance and smooth.
- •The surface should be free of all kinds of oil, grease, rust and paraffin residues that may adversely affect adherence and there should be no loose particles on the surface. Surface defects should be repaired with **CERMIREP R4 T.**



APPLICATION

- •CERMITAPE FPO is adhered with special adhesive mortar on both sides, reinforced with polypropylene carrier.
- •CERMITAPE FPO can be easily and quickly applied to any crack or dilatation joint, it does not require any special equipment.
- •A hot air welding tool is required for splicing tape rolls end to end.

SAFETY INSRUCTIONS

·Users should refer to the material safety data sheet (MSDS) of the product, which includes and safety-related information, for information and advice on the safe transport, storage and disposal of chemical products.

Note: Technical values and application instructions are valid under ambient temperature of 23% with relative humidity 50% and they are the results of our tests and experience in accordance with international standards. Our company is not responsible for any errors that may occur if the instructions and recommendations specified in the technical data sheets are not followed.



CERMIX Produced by Koramic Yapı Kimyasalları under license of Cermix SA. www.cermix.com.tr * www.koramic.com.tr Tarsus Factory Head Office Bozüyük Factory

Koramic Yapı Kimvasalları San. Tic. A.S. E-5 Karayolu Üzeri, Şifa Mah. Hükümet Cad. Tuzla 34941 İstanbul / TÜRKİYE

Bozüyük Organize San. Böl. 10. Cad. 106 Ada / 5 Parsel No: 3 Bozüyük - BİLECİK / TÜRKİYE Phone: +90.228.314 63 00 Phone: +90.216.423 34 33 • Fax: +90.216.423 53 63 Fax +90.228.314 63 0

Huzurkent Tarsus Organize Sanavi Bölgesi 13. Cadde No: 10 Tarsus - MERSIN / TÜRKİYE Phone: +90.324.676 40 41-676 42 32-676 44 49 Fax: +90.324.676 40 47